



Premium Panel

NORBOND™ NB220-0155-500

Technical Data Sheet

Upper Skin Material	E-Glass / Epoxy Resin
Lower Skin Material	E-Glass / Epoxy Resin
Core Material	Aramid Fiber Paper
Core Density	1/8 inch cell size; 3.0 lb/ft ³
Max Weight	0.565 lb/ft ²
Typical Weight	0.529 lb/ft ²
Panel Thickness	0.500 in. ± 0.010 in.
Warpage^[1]	0.025 in. maximum

Tested Physical Properties ^[2]	Test Results Value ^[2]		Failure Mode ^[2]	Tested IAW ^[2]
	A-Basis	B-Basis		
Long Beam Flexure ^[3]				
"L" Direction Skin Stress, psi	26,749	30,016	Upper Skin Compression	ASTM C 393 ASTM D 7249
"L" Direction P/Y, lb/in	205	227		
"W" Direction Skin Stress, psi	30,513	33,219		
"W" Direction P/Y, lb/in	148	152		
Short Beam Shear ^[3]				
"L" Direction Stress, psi	151	161	Core Shear	ASTM C 393
"W" Direction Stress, psi	101	107		
Stabilized Core Compression, psi	253	285	Core Crush	ASTM C 365

Panel meets FAR 25.853(a)'s 60-second vertical burn requirements.

- 1: Panel warpage is measured as a maximum deviation from a straight line in a 4-foot span.
- 2: FAA approved allowables' data, per applicable FAA Form 8110-3, which is available upon request.
- 3: All data was calculated using a skin thickness of .020 inches.

DISCLAIMER: The data is provided "AS IS, WHERE IS, ALL FAULTS (IF ANY) INCLUDED". NORDAM MAKES NO WARRANTY WHATSOEVER, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR PURPOSE, CONCERNING THE DATA OR THE PRODUCTS. This data sheet is subject to change without notice. It is the user's responsibility to verify that the data sheet is the most current data sheet available. All products supplied are subject to NORDAM's standard terms and conditions of sale.

NORDAM PROPRIETARY INFORMATION. ACCESS & USE SUBJECT TO NORDAM'S FULL WARNING & RESTRICTION AT THE HEAD OF THIS DOCUMENT. REMOVAL OR ALTERATION OF THE FULL WARNING OR RESTRICTION MAKES THIS AN ILLEGAL COPY. 9E991 AT01