

Premium Panel

NORBOND™ NB221-0155-500

Technical Data Sheet

Upper Skin Material	E-Glass / Phenolic Resin			
Lower Skin Material	E-Glass / Phenolic Resin			
Core Material	Aramid Fiber Paper			
Core Density	1/8 inch cell size; 3.0 lb/ft ³			
Max Weight	0.565 lb/ft ²			
Typical Weight	0.529 lb/ft ²			
Panel Thickness	0.500 in. ± 0.010 in.			
Warpage ^[1]	0.025 in. maximum			

Tested Physical Properties ^[2]	Test Results Value ^[2]		Failure Mode ^[2]	Tested IAW ^[2]
	A-Basis	B-Basis		
Long Beam Flexure ^[3]				
"L" Direction Skin Stress, psi	22,487	27,729		
"L" Direction P/Y, lb/in	130	151	Upper Skin	ASTM C 393
"W" Direction Skin Stress, psi	14,867	17,758	Compression	ASTM D 7249
"W" Direction P/Y, lb/in	125	146		
Short Beam Shear ^[3]				ECT
"L" Direction Stress, psi	128	146	Core Shear	ASTM C 393
"W" Direction Stress, psi	67.6	80.4		
Stabilized Core Compression, psi	134	234	Core Crush	ASTM C 365

Panel meets FAR 25.853(a)&(d)'s 60-second vertical burn requirements, 65/65 heat release and smoke density requirements.

1: Panel warpage is measured as a maximum deviation from a straight line in a 4-foot span.

2: FAA approved allowables' data, per applicable FAA Form 8110-3, which is available upon request.

3: All data was calculated using a skin thickness of .020 inches.

ncontrolled Copy

DISCLAIMER: The data is provided "AS IS, WHERE IS, ALL FAULTS (IF ANY) INCLUDED". NORDAM MAKES NO WARRANTY WHATSOEVER, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR PURPOSE, CONCERNING THE DATA OR THE PRODUCTS. This data sheet is subject to change without notice. It is the user's responsibility to verify that the data sheet is the most current data sheet available. All products supplied are subject to NORDAM's standard terms and conditions of sale.

ted

On:

Prin

©The NORDAM Group, Inc. 6910 N. Whirlpool Drive, Tulsa, OK 74117 918-401-5000

8