

Premium Panel NORLAM™ NL610-10633-750

Technical Data Sheet

Upper Skin Material	2024-T3 Aluminum Clad			
Lower Skin Material	2024-T3 Aluminum Clad			
Core Material	5052 Aluminum Core			
Core Density	3/16 inch cell size; 4.4 lb/ft³			
Max Weight	1.089 lb/ft ²			
Typical Weight	0.962 lb/ft ²			
Panel Thickness	0.750 in. ± 0.010 in.			
Warpage ^[1]	0.025 in. maximum			

Tested Physical Properties ^[2]	Results Value ^[2]		Failure Mode ^[2]	Tested IAW ^[2]
	A-Basis	B-Basis		
Long Beam Flexure ^[3]				
"L" Direction Skin Stress, psi	51,679	56,988		
"L" Direction P/Y, lb/in	654	867	Upper Skin	ASTM C 393
"W" Direction Skin Stress, psi	44,264	49,036	Compression	ASTM D 7249
"W" Direction P/Y, lb/in	883	973		
Short Beam Shear ^[3]				
"L" Direction Stress, psi	236	286	Core Shear	ASTM C 393
"W" Direction Stress, psi	134	158		
Stabilized Core Compression, psi	317	380	Core Crush	ASTM C 365

Panel meets FAR 25.853(a)'s 60-second vertical burn requirements.

- 1: Panel warpage is measured as a maximum deviation from a straight line in a 4-foot span.
- 2: FAA approved allowables' data, per applicable FAA Form 8110-3, which is available upon request.
- 3: All data was calculated using a skin thickness of .020 inches.

DISCLAIMER: The data is provided "AS IS, WHERE IS, ALL FAULTS (IF ANY) INCLUDED". NORDAM MAKES NO WARRANTY WHATSOEVER, EXPRESSED OR IMPLIED, INCLUDING WITHOUT LIMITATION ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR PURPOSE, CONCERNING THE DATA OR THE PRODUCTS. This data sheet is subject to change without notice. It is the user's responsibility to verify that the data sheet is the most current data sheet available. All products supplied are subject to NORDAM's standard terms and conditions of sale.

NORDAM PROPRIETARY & COMPANY CONFIDENTIAL INFORMATION. ACCESS & USE SUBJECT TO NORDAM'S FULL WARNING & RESTRICTION AT THE HEAD OF THIS DOCUMENT. REMOVAL OR ALTERATION OF THE FULL WARNING OR RESTRICTION MAKES THIS AN ILLEGAL COPY. EAR99 AT01

©The NORDAM Group, Inc.

OR AL
6910 N. Whirlpool Drive, Tulsa, OK 74117

918-401-5000

Revision NC 9/5/2018 DS-NL610-10633-750